

ZORROCRACKFIX | 009C

Crack Filler

009C

ZORROCRACKFIX
Crack Filler



READY TO USE PASTE FILL CRACKS FOR INTERNAL & EXTERNAL SURFACES IN PLASTER

ZORROCRACKFIX 009C is high quality weather durable acrylic based ready to use flexible putty which is easy to use for filling cracks in plastered surfaces because it has excellent bonding, ease of application, durability, water resistance & aesthetic appearance.

AREAS OF APPLICATION

- Repairing of internal and external cracks in plastered surfaces up to 5 mm X 5 mm size.
- Suitable for both vertical and horizontal applications wherever hairline cracks are observed.
- It can be used for leveling the undulations of the un-plastered or plastered ceilings & walls before painting.

PRECAUTIONS AND LIMITATIONS

- ZORROCRACKFIX 009C is strictly not recommended to fill cracks more than 5 mm.
- Strictly not for filling structural cracks/ expansion joints/construction joints/separation gaps.
- Painting work can be done after 24 hours.

COVERAGE

Approx. 25 RMT/kg for 5 mm X 5 mm crack depending on site conditions.

STORAGE

Away from moisture and heat.

SHELF LIFE & STORAGE

12 months from the date of manufacturing in unopened containers.

PACKAGING

500gm and 1kg



AIPL MARKETING PVT. LTD.

409, 4th Floor, D-Mall, Netaji Subhash Place,
Opp. Wazirpur DTC Depot, Delhi-110034

For Consumer Complaint Please Contact : 011- 49010190
Mob: +91 8595167806. Email: info@aiplzorro.com

www.aiplzorro.com



CONSTRUCTION CHEMICALS FOR WATERPROOFING & REPAIR



007L

ZORROPROOF
Liquid Waterproofing Product

008W

ZORROCRETE
Waterproofing & Repair Product

009C

ZORROCRACKFIX
Crack Filler

ZORROPROOF | 007L

Liquid Waterproofing Product



007L

ZORROPROOF
Liquid Waterproofing Product

Liquid integral waterproofing compound for concrete and mortar.

AREAS OF APPLICATION

Water reducing and waterproofing admixture for all types of concrete and mortar. It is used for waterproofing of concrete and sand cement mortar used in basements, roof slabs, screeds, water retaining structures, beams, columns, culverts, tunnels, sunken slabs, terrace slabs, water tanks, sewerage works etc.

PRECAUTIONS & LIMITATIONS

- Don't add ZORROPROOF 007L directly to dry cement & aggregate mix.
- Water-cement ratio to be maintained as low as possible.
- Don't increase the dosage of ZORROPROOF 007L than recommendation.

DOSAGE

200ml for 50kg bag of Cement.

PACKAGING

ZORROPROOF007L LWP is available in 200 ml, 1 ltr, 5 ltr, 10 ltr & 20 ltr containers.

SHELF LIFE & STORAGE

Shelf life 24 months from the date of manufacturing. Store in a cool dry place in unopened condition . (Prevent from direct sunlight)



ZORROCRETE | 008W

Waterproofing & Repair Product



008W

ZORROCRETE
Waterproofing & Repair Product

ZORROCRETE 008W is Styrene Butadiene Rubber based bonding agent.

APPLICATION AREAS

- For waterproofing of Roof Slabs, Sunken Slabs, Basements, Water Tanks, Balconies, Sunshades etc.
- It is used as a Bonding Agent between old & new concrete for cementitious substrates.
- It is also effective to make repair mortars & concrete in building rehab work.
- Treatment for leaching & salt petre action.
- It is multipurpose mortar admixture for injection grouts.

COVERAGE/DOSAGE

		COVERAGE*
AS A PASSIVATOR COAT	1:1 (Zorrocrete 008W: Cement)	2-3 Rmtr/ kg for 25 mm dia bar at 1 mm thickness
AS A WATERPROOF COATING	1:1.5 (Zorrocrete 008W : Cement)	1.5 - 2 m ² / kg for 2 coat at 0.5-0.6 mm thickness
AS BONDING COAT	1:1 (Zorrocrete 008W : Cement)	2-3 m ² / kg



TO KNOW MORE
**CALL ZORRO
EXPERT**

08595167806

APPLICATION

Wide range of mix designs are recommended for different application using AIPL ZORROCRETE 008W.

SR NO.	APPLICATION	COMPOSITION	QUANTITY OF ZORROCRETE 008W	CONSISTENCY & THICKNESS
1.	Patching & repair mortar & plaster for masonry	*OPC-50 Kg *Graded sharp & washed & dry sand-150 kg *Water- 11 to 15 litres	5 to 9 kg	Mortar consistency, 8 to 30 mm thickness
2.	Heavy duty floor screed	*OPC-50 kg *3-6 mm granite chips 75 kg. *Graded sharp & washed sand-75kg. *Water - 8-12 litres	5 to 9 kg	Semi dry cohesive consistency, 10-25 mm thickness
3.	Renders	*OPC-50kg * Graded sharp & washed sand-150kg. *Water- 10-15 litres	5 kg	Mortar consistency, 6-9 mm thickness
4.	Bonding mortar for slip bricks & tiles	*OPC-50 kg *Graded sharp & washed sand-125 kg *Water- 10-15 litres	5 to 7.5 kg	Mortar consistency, 6-40 mm thickness

PRECAUTIONS & LIMITATIONS

- Consume mixed material within 45 minutes.
- Moisten the surface adequately before coating application.
- Do not apply coating over loose or cracked plaster surface.
- Do not add extra water or more than recommended dosage.
- Recommended dosage to be followed to achieve desired results.

PACKAGING

500 gm, 1 kg, 5 kg, 10 kg & 20 kg

SHELF LIFE & STORAGE

Shelf life 18 months from the date of manufacturing. Store in a cool dry place in unopened condition . (Prevent from direct sunlight)

